



| Technical datas Ordinary PLYWOOD 18mm |                               |                 |       |               |                        |
|---------------------------------------|-------------------------------|-----------------|-------|---------------|------------------------|
| NO                                    | Property                      |                 | Unit  | Test Method   | Value of Test          |
| 1                                     | Moisture Content              |                 | %     | EN322         | 8-12                   |
| 2                                     | Density                       |                 | kg/m3 | EN322         | 530                    |
| 3                                     | Bonding Quality               | Bonding Quality | Mpa   | EN314         | Max: 1.32<br>Min: 0.85 |
|                                       |                               | Damage Rate     | %     | GB/T9846-2015 | 60%                    |
| 4                                     | Bending Modules of Elasticity | Longitudinal    | Mpa   | EN310         | 6800                   |
|                                       |                               | Lateral         |       |               | 5920                   |
| 5                                     | Bending Strength N/mm         | Longitudinal    | Mpa   | EN310         | 63                     |
|                                       |                               | Lateral         |       |               | 48                     |

Со почит,

